



## HARD MAPLE TORONTO

Canadian Maple, three strip design, silk matte finish, cleaner graining and color variation than Hard Maple Manitoba. - SPECIAL ORDER

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Article Number	153N15AP50KW 0	Wood Species	Hard Maple	Moisture	EN13183	7%±2%
EAN Code	7393969018838	Design	3-strip	content		
Surface Treatment	Silk matte finish	Grading	Calm	Minimun Mean Density kg/m³ >500 kg/m³		
Dimensions	95 3/8 x 7 7/8 x 5/8"	Range	Kährs Original	Reaction To Fire	EN13501-1	Dfl-s1
Weight per Package	50.7 lbs	Collection	American Naturals Collection	Formaldehyde	EN717-1	E1
Area per Package	31.2 sqft		Concetion	Emission		
Area per pallet (m²)	0 sqft	Resandable	2 times	Content PCP	CEN/TR14823	3 ≤ 5 x 10-6n
Package info	Packages may contain start and stop boards.	Natural/Stained	Natural	Breaking EN1533 Strength N/mm²	EN1533	NPD
		Brinell Value	4,8			
		Joint	Woodloc® 5S			
DETAIL DESCRIPTION		Floor heating	No	<ul><li>Thermal Conductivity</li></ul>	EN12664	0,14 W/mK
Even colour with minor variations. Small sized knots in limited numbers allowed.			30 years	Thermal Resista	ance R-Value	.11 (m2K/W)
		Wear-layer material	Hardwood	Biological	EN350-2	Class 1
COLOR CHANGE		Wear-layer thickness	1/8"	Durability		
Changes from cream white to golden cream.		Core material	Pine/Spruce lamella	CARB2		Compliant
		Thickness	5/8"			
		Installation method	Floating, Glue-Down			



Lucas: 773 987 5994 Peter: 847 778 2445 ADDRESS:

466 Diens Drive, Wheeling, 60090, Illinois https://www.majestictiles.com contact@majestictiles.com

## **CERTIFICATES**







## **Descriptions & Imagery**

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.